

TEST REPORT

NUMBER : DELT11012676

DATE : 01-Apr-2011

APPLICANT : STUPA TRADING COMPANY/KATHMANDU

THOMEL - 29, KATHMANDU, NEPAL, -

ATTN : NABIN CHITRAKAR.

Sample Description : ONE PIECE OF SUBMITTED WOVEN FABRIC SAMPLE IN
COLOR MULTI.Applicant Provided Care Instructions :
LUKE WARM IRON, HANG DRY

Date Received/Date Test Started : 29 Mar 2011
Date Confirmation Received : -
Destination of Buyer : U.S.A
Style No : COTTON (STR)
Order No : -
Article No : -
Colour : MULTI
Fibre Content : -
Specification No. : -
Type of Finish : -
Fabric Weight : 50 GSM
End Uses : GARMENT
Manufacturer's Name : STUPA TRADING COMPANY/KATHMANDU

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE
REFER TO ENCLOSED PAGE(S)

CONCLUSION :

FLAMMABILITY TEST

M

NOTE : M = MEETS REQUIREMENT, F = FAILS TO MEET REQUIREMENT
* = REQUIREMENT NOT PROVIDED, NA = NOT APPLICABLE

PREPARED & CHECKED BY :
FOR INTERTEK INDIA PRIVATE LIMITED [GURGAON]

AVNISH CHHABRA
SR. MANAGER - LAB

TEX-59

Page 1 of 2

Intertek India Private Limited

290, Udyog Vihar, Phase-II, Gurgaon, Haryana -122016.
Tel : 0124-4503400, Fax : 0124-4303592.

Registered Office : E-20, Block B-1, Mohan Co-Operative Industrial Area, Mathura Road, New Delhi -110044. Web site : www.intertek-labtest.com.

TEST REPORT

NUMBER : DELT11012676
DATE : 01-Apr-2011

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

1. FLAMMABILITY TEST □
16 CFR 1610-2008

<u>SPECIMEN NO.</u>	<u>ORIGINAL</u>	<u>AFTER DRY CLEANING</u> <u>AND WASHING</u>	<u>Requirement</u> Class-1
01	7.4 BB	4.5 BB	
02	7.1 BB	4.2 BB	
03	7.3 BB	4.0 BB	
04	7.0 BB	4.3 BB	
05	7.2 BB	4.6 BB	
AVERAGE	7.2 BB	4.3 BB	
CLASSIFICATION : CLASS 1 [NORMAL FLAMMABILITY]			

REMARK:

BB = ACTUAL TIME OF IGNITION UNTILL THE FLAME BREAKS THE CORD.

END OF THE TEST REPORT