

**TEST REPORT**

NUMBER : DELT11012681

DATE : 01-Apr-2011

APPLICANT : STUPA TRADING COMPANY/KATHMANDU

THOMEL - 29, KATHMANDU, NEPAL, -

ATTN : NABIN CHITRAKAR.

Sample Description : ONE PIECE OF SUBMITTED WOVEN FABRIC SAMPLE IN  
COLOR MULTI STRIPE.

Applicant Provided Care Instructions :  
LUKE WARM IRON, HANG DRY



Date Received/Date Test Started : 29 Mar 2011  
Date Confirmation Received : -  
Destination of Buyer : U.S.A  
Style No : COTTON (STR2)  
Order No : -  
Article No : -  
Colour : MULTI STRIPE  
Fibre Content :  
Specification No. : -  
Type of Finish : -  
Fabric Weight : 60 GSM  
End Uses : GARMENT  
Manufacturer's Name : STUPA TRADING COMPANY/KATHMANDU

TEST CONDUCTED : AS PER THE REQUEST OF THE APPLICANT. FOR FURTHER DETAILS PLEASE  
REFER TO ENCLOSED PAGE(S)

**CONCLUSION :**

Flammability M

NOTE : M = MEETS REQUIREMENT, F = FAILS TO MEET REQUIREMENT  
\* = REQUIREMENT NOT PROVIDED, NA = NOT APPLICABLE

PREPARED & CHECKED BY :  
FOR INTERTEK INDIA PRIVATE LIMITED [GURGAON]

AVNISH CHHABRA  
SR. MANAGER - LAB



TEST REPORT

NUMBER : DELT11012681  
DATE : 01-Apr-2011

TEST CONDUCTED (AS REQUESTED BY THE APPLICANT)

**1. Flammability**  
16 CFR 1610-2008

<u>SPECIMEN NO.</u>	<u>ORIGINAL</u>	<u>AFTER DRY CLEANING AND WASHING</u>	<u>Requirement</u>
1.	6.5 BB	8.5 BB	Class-1
2.	6.8 BB	8.3 BB	
3.	6.3 BB	8.6 BB	
4.	6.5 BB	8.4 BB	
5.	6.2 BB	8.7 BB	
AVERAGE	6.5 BB	8.5 BB	
CLASSIFICATION :	CLASS 1 [NORMAL FLAMMABILITY]		

REMARK:

BB = ACTUAL TIME OF IGNITION UNTILL THE FLAME BREAKS THE CORD.

---

## END OF THE TEST REPORT ##